



PRODUCT DATA

Brand Name: TZ40-DOL

Description: High purity sintered dolomite that is sized, blended with zirconia, pressed into a brick shape for rotary kilns, then fired in a high temperature tunnel kiln to create a strong ceramically bonded brick. TZ40-DOL is a high quality, spall and corrosion resistant refractory for use in the upper and lower transition zone of a rotary kiln.

Physical properties shown are averages based on standard brick sizes.
ASTM test methods used where applicable

Bulk Density (pcf)

As Received 181 (2.90 g/cm³)

Cold Crushing Strength (psi)

At 70°F (21°C) 3600 (252 kg/cm²)

Apparent Porosity (%)

As Received 15.0

Thermal Conductivity (K Factor)

Mean Temperature	BTU/ft ² /hr./°F/inch	W/mK
1242°F (700°C)	24.3	3.5
1832°F (1000°C)	20.8	3.0

Typical Chemical Analysis (%)

(Calcined Basis)

Magnesia (MgO)	47.0
Lime (CaO)	48.0
Alumina (Al ₂ O ₃)	0.8
Silica (SiO ₂)	1.2
Iron Oxide (Fe ₂ O ₃)	1.3
Zirconia (ZrO ₂)	1.7

Packaging and Storage: Pallets should be stored in a dry protected area. Vacuum sealed ALUVAC foil packaging is available upon request for optimum shelf life. Care should be taken not to damage outer packaging.

Brand Code: 5019

The properties shown on this data sheet represent typical average results using standard ASTM test methods (unless otherwise noted) conducted under controlled condition (using standard rectangular shapes), and should not be considered to be guaranteed specifications. Properties are subject to normal manufacturing statistical standard deviation ranges, and Resco Products, Inc. reserves the right to modify the properties and specifications at any time without prior notice.

RESCO PRODUCTS disclaims any express or implied warranties based on this sheet.

12/19/16 is the date that this data sheet was updated. Check with your RESCO sales representative or RESCO website to determine you have the current sheet.