



PRODUCT DATA

Brand Name: **UNIFORM 70LC**

Description: UNIFORM 70 LC is a precast shape made with a 70% Alumina, Low Cement Castable. For added strength and spalling resistance, UNIFORM 70 LC is available with stainless steel fiber additions.

Physical properties shown are average values of samples taken under controlled conditions
ASTM test methods used where applicable

Maximum Service Temperature: 3100°F (1705°C)

| | Pre-Cast Data | |
|--|---------------|---------------------------|
| <u>Bulk Density (pcf)</u> | | |
| After 230°F (110°C) | 157 | (2.51 g/cm ³) |
| <u>Modulus of Rupture (psi)</u> | | |
| After 230°F (110°C) | 1500 | (105 kg/cm ²) |

Typical Chemical Analysis (%)

(Calcined Basis)

| | |
|---|------|
| Alumina (Al ₂ O ₃) | 70.2 |
| Silica (SiO ₂) | 25.3 |
| Iron Oxide (Fe ₂ O ₃) | 1.0 |
| Titania (TiO ₂) | 2.1 |
| Lime (CaO) | 1.0 |
| Magnesia (MgO) | 0.2 |
| Alkalies (Na ₂ O+K ₂ O) | 0.2 |

Brand Code: 3688

The properties shown on this data sheet represent typical average results using standard ASTM test methods (unless otherwise noted) conducted under controlled condition (using standard rectangular shapes), and should not be considered to be guaranteed specifications. Properties are subject to normal manufacturing statistical standard deviation ranges, and Resco Products, Inc. reserves the right to modify the properties and specifications at any time without prior notice.

RESKO PRODUCTS disclaims any express or implied warranties based on this sheet.

03/30/17 is the date that this data sheet was updated. Check with your RESKO sales representative or RESKO website to determine you have the current sheet.