

PRODUCT DATA

Brand Name:

VIBROCAST FS-6

Description:

VIBROCAST FS-6 is a Low Cement, Fused Silica-based Castable that can be installed by vibration cast methods only. This product features excellent resistance to thermal cycling conditions.

Physical properties shown are average values of samples taken under controlled conditions ASTM test methods used where applicable

Maximum Service Temperature: 2000°F (1095°C) Thermal Cycling

Typical Water Required for Mixing (by weight) : Vibration Casting	6.2%	
Vibration Casting	Vibration Cast Data	
Bulk Density (pcf)		
After 220°F (105°C)	125	(2.00 g/cm ³)
After 1500°F (815°C)	124	(1.98 g/cm ³)
Cold Crushing Strength (psi)		
After 1500°F (815°C)	8000	(560 kg/cm ²)
Permanent Linear Change (%) After 1500°F (815°C)	-0.2 to 0.0	
Thermal Conductivity (K Factor)		
Mean Temperature 1000°F (540°C)	<u>BTU/ft²/hr./°F/inch</u> 7.8	<u>W/mK</u> 1.12
1500°F (815°C)	7.5	1.08
2000°F (1095°C)	7.7	1.11
<u>Typical Chemical Analysis (%)</u> (Calcined Basis)		
Alumina (Al ₂ O ₃)	19.9	
Silica (SiO ₂)	77.7	
Iron Oxide (Fe ₂ O ₃)	0.3	

Silica (SiO ₂)	77.7
Iron Oxide (Fe ₂ O ₃)	0.3
Titania (TiO ₂)	0.3
Lime (CaO)	1.7
Magnesia (MgO)	0.1
Alkalies (Na ₂ O+K ₂ O)	0.2

Standard Packaging: 55 lb bag. 72 bags per pallet. Bulk packaging available.

Brand Code: 0427

The properties shown on this data sheet represent typical average results using standard ASTM test methods (unless otherwise noted) conducted under controlled condition (using standard rectangular shapes), and should not be considered to be guaranteed specifications. Properties are subject to normal manufacturing statistical standard deviation ranges, and Resco Products, Inc. reserves the right to modify the properties and specifications at any time without prior notice.

RESCO PRODUCTS disclaims any express or implied warranties based on this sheet.

04/03/17 is the date that this data sheet was updated. Check with your RESCO sales representative or RESCO website to determine you have the current sheet.

One Robinson Plaza - Suite 300, 6600 Steubenville Pike, Pittsburgh, PA, 15205 Phone: 888-283-5505