



# PRODUCT DATA

Brand Name:

**UNIFORM 60M**

Description:

Uniform 60M is a Low Cement, 60% Alumina Precast Shape

Physical properties shown are average values of samples taken under controlled conditions  
ASTM test methods used where applicable

**Maximum Service Temperature: 3100°F (1705°C)**

## Bulk Density (pcf)

After 220°F (105°C)	152	(2.43 g/cm <sup>3</sup> )
After 650°F (343°C)	151	(2.42 g/cm <sup>3</sup> )
After 1500°F (815°C)	151	(2.42 g/cm <sup>3</sup> )

## Cold Crushing Strength (psi)

After 1500°F (815°C)	11,600	(816 kg/cm <sup>2</sup> )
----------------------	--------	---------------------------

## Modulus of Rupture (psi)

After 650°F (343°C)	1,163	(82 kg/cm <sup>2</sup> )
---------------------	-------	--------------------------

## Permanent Linear Change (%)

After 650°F (343°C)	-0.1 to 0.0
---------------------	-------------

## Typical Chemical Analysis (%)

(Calcined Basis)

Alumina (Al <sub>2</sub> O <sub>3</sub> ) .....	58.6
Silica (SiO <sub>2</sub> ) .....	36.7
Iron Oxide (Fe <sub>2</sub> O <sub>3</sub> ) .....	0.8
Titania (TiO <sub>2</sub> ) .....	1.8
Lime (CaO) .....	1.5
Magnesia (MgO) .....	0.1
Zirconia (ZrO <sub>2</sub> ) .....	0.3
Alkalis (Na <sub>2</sub> O+K <sub>2</sub> O) .....	0.2

Brand Code: 4496 4134 (w/ 1.5% ss fibers)

The properties shown on this data sheet represent typical average results using standard ASTM test methods (unless otherwise noted) conducted under controlled condition (using standard rectangular shapes), and should not be considered to be guaranteed specifications. Properties are subject to normal manufacturing statistical standard deviation ranges, and Resco Products, Inc. reserves the right to modify the properties and specifications at any time without prior notice.

RESCO PRODUCTS disclaims any express or implied warranties based on this sheet.

04/25/19 is the date that this data sheet was updated. Check with your RESCO sales representative or RESCO website to determine you have the current sheet.